



Square Rubber Tile

PRODUCT SUBMITTAL

Nominal Dimensions	18" (45.7 cm) x 18" (45.7 cm) x 1/8" (3.2 mm)
Finish	Smooth with Raised Square Disc
ASTM F1344 – Rubber Floor Tile	Type 1 A & B, Grade 1
ASTM E648 (NFPA 253) – Critical Radiant Flux	Class 1, > 0.45 W/cm ²
ASTM E662 (NFPA 258) – Smoke Density	Passes, < 450
CAN/ULC-S102.2 – Surface Burning	115 Flame Spread Rating 275 Smoke Developed Classification
ASTM D2047 – Static Coefficient of Friction	> 0.60
ASTM F970 – Static Load Resistance	Passes less than .005" Indentation after 250 psi
ASTM F970 – Static Load Resistance (Modified)	Passes less than .005" Indentation after 1100 psi
ASTM F925 – Chemical Resistance	Excellent with chemicals listed in standard, Additional chemicals available via chart
ASTM F1514 – Heat Stability	Excellent, ΔE < 8 average
ASTM D3389 – Abrasion Resistance	Excellent, < 1 g loss after 1000 cycles
ASTM G21 – Resistance to Fungi	Excellent, No Growth
ASTM E492/E989 – Impact Sound Transmission	IIC 51 (6" Concrete, Gypsum Drop Ceiling)
ASTM E90/E413 – Airborne Sound Transmission	STC 63 (6" Concrete, Gypsum Drop Ceiling)
ASTM E2179 – Effectiveness of Floor on Impact Sound Transmission	ΔIIC 9
Acclimation Time	48 Hours, see installation instructions for details
Service & Storage Temperature	65° - 85° F, see installation instructions for details
Sustainability Information	Contributes to LEED v4/4.1 Meets CA 01350 Requirements FloorScore Certification*
Warranty	10 Year, see warranty document for details
Recommended Adhesives	Excelsior SP-500, Pressure Sensitive Spray Excelsior AW-510, Wet-Set Acrylic Excelsior AP-520, Pressure Sensitive Roll/Trowel Excelsior MS-700, Modified Silane Wet-Set Excelsior U-705, Urethane Wet-Set
Technical Support	solutions@rhctechnical.com
Product Support	support@procedoflooring.com
Technical Documentation	www.procedoflooring.com

*certificate or document available on website